

SHAOXING YIWAY IMPORT AND EXPORT CO.,LTD.  
ROOM NO.1904, 19TH FLOOR OF DINGSHENG MANSION,NO.375 OF EAST SHEN GLI  
ROAD,SHAOXING,ZHEJIANG,CHINA

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Woven fabric ((A)Woven fabric(Woven blackout P/D B1))

Buyer : WOUTERS TEXTIELHANDEL B.V.

Sample Color : (A)Navy

Style No. : A02768

Proposed Care Instruction : -


Sample Receiving Date : May 26, 2026

Testing Period : May 26, 2026 - Jun 16, 2026

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of  
SGS-CSTC Standards Technical Services (Changzhou) Co., Ltd



Susan Dong (Account Executive)



Test Result

**Textiles and Textile Products - Burning Behaviour - Curtains and Drapes -Classification Scheme#**  
(EN 13773:2003)

Sample: A

**Class specification:** Class 1

**Detailed Procedure to Determine the Ignitability of Vertically Oriented Specimens(Small Flame)**  
(EN 1101:1995+A1:2005 (Modified); EN ISO 6940:1995)

After 100 washes

| Ignition time (s) | Lengthwise | Widthwise |
|-------------------|------------|-----------|
| 1                 | N          | N         |
| 2                 | N          | N         |
| 3                 | N          | N         |
| 4                 | N          | N         |
| 5                 | N          | N         |
| 10                | N          | N         |
| 15                | N          | N         |
| 20                | N          | N         |

Remark:

- (1) "Y" : Ignition ; "N" : Non-ignition
- (2) Ignition shall be deemed to have occurred if flaming of the specimen which gives an Afterflame time of 5s or more or which reaches the top or vertical edges in less than 5s.
- (3) Burner ignition location: Bottom edge ignition
- (4) Ignition time: 1-5s, 10s, 15s, 20s
- (5) Gas used: Propane

**Textiles and textile products -Burning behaviour - Curtains and drapes - Measurement of flame spread of vertically oriented specimens with large ignition source**  
(EN 13772:2011)

After 100 washes

| Specimen             | Lengthwise |   |   | Widthwise |   |   |
|----------------------|------------|---|---|-----------|---|---|
|                      | 1          | 2 | 3 | 1         | 2 | 3 |
| T1 severed (Y/N)     | N          | N | N | N         | N | N |
| T3 severed (Y/N)     | N          | N | N | N         | N | N |
| T1 (seconds)         | /          | / | / | /         | / | / |
| T3 (seconds)         | /          | / | / | /         | / | / |
| Flaming debris (Y/N) | N          | N | N | N         | N | N |

Remark:

- (1) T1: From the start of the application of the igniting flame to the severance of the first marker thread (240mm)
- (2) T3: From the start of the application of the igniting flame to the severance of the third marker thread (540mm)



- (3) Y= Yes; N=No
- (4) Burner ignition location: Bottom edge ignition.
- (5) Ignition time: 10s.
- (6) Gas used: Propane

Classification for EN 13773:

| Class | Ignitability                      | Flame spread   |
|-------|-----------------------------------|--|
| 1     | Non ignition according to EN 1101 | 1 <sup>st</sup> marker threads not severed, no flaming debris, according to EN 13772 |
| 2     | Non ignition according to EN 1101 | 3 <sup>rd</sup> marker threads not severed, no flaming debris, according to EN 13772 |
| 3     | Non ignition according to EN 1101 | 3 <sup>rd</sup> marker threads severed, and/or flaming debris, according to EN 13772 |
| 4     | Ignition according to EN 1101     | 3 <sup>rd</sup> marker threads not severed, no flaming debris, according to EN 1102  |
| 5     | Ignition according to EN 1101     | 3 <sup>rd</sup> marker threads severed, and/or flaming debris, according to EN 1102  |

**Conclusion:**

The submitted sample **complies** with the requirement of Class 1 prescribed in EN 13773:2003.

Wash procedure: ISO 6330:2021; After 100 washes, Using horizontal axis, front-loading type machine; Procedure No.4N, Machine Wash At 40°C; with 2kg total dry mass (Type III (100% Polyester) Ballast+ Specimen), 20±1 g ECE reference detergent 98 without optical brightener, Tumble Dry Normal, Not Exceeding 80°C

#This test was carried out by SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd.

**Sample Photo**



\*\*\*End of Report\*\*\*



Scan to see the report



SL42604313384601TX

Verification:  
[check.sgsonline.com.cn](http://check.sgsonline.com.cn)

